



Architects Specifications
For Copying And Pasting Into
Your Own Specifications
Can Be Found At The End Of
This Sheet

WHIPPLETREE PRODUCT INFORMATION & SPECIFICATION SHEET

English Oak – Log Sawn Plank ‘B’ GRADE JOINERY WANNEY EDGED

DESCRIPTION

Relegated Joinery Grade due to light defects or imperfections. Ideal where light character or rustic detail is required. Used for internal and external joinery, supplied as un edged boards.

Technical Specifications – English Oak ‘B’ Grade Joinery Waney Edged

Lengths	2m up to 6m
Widths (mm)	In thicknesses of 20 to 38 mm – the width of the log In thicknesses of 50 to 150mm - half the width of the log
Thickness (mm)	20, 26 , 32 , 38, 50, 63, 75, 100, 125 ,150
Colour	Usual light oak, occasional darker streaking
Knot size	Generally up to 50mm – occasionally larger, if sound
Suggested waste factor	100%
Grade	Character – Wild grain, sound knots, pippy knots, occasional non-structural splits
Availability	5-7 days
Moisture content	Aid dried 18% - Kiln dried 10 -12%
Weight	1.35m ³ per Tonne
Quarter sawn	Available as special selection
Measurement	All w/edge is sold by “Full board measurement” (i.e. including sap and half the wane



Architects Specifications
For Copying And Pasting Into
Your Own Specifications
Can Be Found At The End Of
This Sheet

WHIPPLETREE PRODUCT INFORMATION & SPECIFICATION SHEET

Warnings/Cautions/Recommendations

If you wish to select waney edged boards, always make an appointment to visit as we have to arrange for the correct packs to be lifted from our stocks to allow you easy access.

We do not select waney edged boards to make a customer's cutting list. Boards are selected as 'random'. Please specify typical lengths and the volume required and we will then select enough 'volume' to cover your requirement.

If a customer requires a lump sum price for waney edged we calculate it based on the volume required plus 100% waste. In this situation it is generally more cost effective to buy sawn to size for the same value and this will save you considerable sorting and cutting time on site.

We cannot guarantee special widths in waney edged, you may need to join narrow boards to create the widths you want. If we find the widths you want in the pack, it's a bonus!

When buying waney edged, if the board looks good, but when re sawn shows a defect, this is part of your wastage.

Any boards wider than 225mm or longer than 3m are subject to surcharges.



Architects Specifications
For Copying And Pasting Into
Your Own Specifications
Can Be Found At The End Of
This Sheet

WHIPPLETREE PRODUCT INFORMATION & SPECIFICATION SHEET

Commonly Asked Questions

CAN YOU GIVE US A LUMP SUM COST FOR WANNEY EDGED?

Yes, if you can tell us how much volume you need including wastage. If you can give us is a cutting list, we will price it as sawn to size. If you then decide to come and select waney edged boards to give you a lower waste factor, you may well gain!

Custom Ordering Advice

Always order the length you will be using, do not add lengths together and order the longer lengths as longer lengths are more expensive per metre. In other words, you will save money if you order two 1.50 metre lengths rather than one 3.00 metre length which you then cross cut to two 1.50 lengths. Always try to give us the cutting list you actually need to do the job and we will find the most cost effective way to supply it to you.

Tell us what you plan to make and what the various sizes are for i.e. doors or window sills or jambs etc.

Architects Specifications Follow:



Architects Specifications
For Copying And Pasting Into
Your Own Specifications
Can Be Found At The End Of
This Sheet

WHIPPLETREE PRODUCT INFORMATION & SPECIFICATION SHEET

Architects Specifications:

(Please copy and paste into your specifications as required)

Option 1 – Air Dried

Timber will be joinery 'B' grade waney edged consisting of quality English Oak with full traceability and evidenced by a Certificate Of Origin from Whippletree (Tel: 01763 208966). The timber will have generally straight grain with occasional wild grain, sound tight knots, some surface checking or occasional splits. Slight sap is acceptable but the timber will be free of all heart defects. Timber will be naturally seasoned to a moisture content of 18-20%. Timber will be stored on site in an area that will allow the timber to remain at this moisture content.

Option 2 – Kiln Dried

Timber will be joinery 'B' grade waney edged consisting of quality English Oak with full traceability and evidenced by a Certificate Of Origin from Whippletree (Tel: 01763 208966). The timber will have generally straight grain timber with occasional wild grain, sound tight knots, some surface checking or occasional splits. Slight sap is acceptable but the timber will be free of all heart defects. Timber will be kiln dried to a moisture content of 10-12% or 18-20% for timber over 50mm thick. Timber will be stored on site in an area that will allow the timber to remain at this moisture content.